



# Tile adhesive and grout for walls

### **DESCRIPTION**

Ready-mixed, non-slip water-resistant tile adhesive and grout for walls.

#### Use for

- Fixing ceramics (up to 300x300mm), mosaics and some natural stone in dry or wet interior environments.
- For domestic areas including showers/kitchens/bathrooms.
- Suitable for heavy duty wet areas including communal showers and commercial kitchens.

#### **Restrictions: NOT suitable for**

- Exterior use or total immersion areas (e.g. swimming pools).
- Not suitable for floors.
- Non-porous tiles.
- Bedding depths exceeding 3mm.
- Grouting for power showers or commercial applications.

### PRODUCT INFORMATION

Composition: Acrylic based organic dispersion

Colour: White

Type/Classification: Exceeds BS EN 12004 D2TE - Dispersion

(ready-to-use), Improved / Additional Characteristics,

Reduced Slip, Extended Open-Time Pack size: 10ltr, 5ltr and 2.5ltr

# Key features:

- Ready-to use
- One product for both adhesive and grout (grout for domestic environments)
- Non-slip (no battens required)
- High bond strength

Grout after: 24 hours (at 20°C)

# **USAGE & SERVICE CONDITIONS**

Walls	✓	Floor	×
Interior	✓	Exterior	×
Dry	✓	Wet (3)(6)	$\checkmark$
Domestic	✓	Worktops	✓
Showers (a)(3)(6)		(1)	
Communal	×	Power	
Showers		showers	
		(3)(7)	

- (1) Tiles must be grouted using BAL EASYPOXY AG.
- (2) Provided the surface is sufficiently flat.
- (3) In wet conditions tank out with BAL TANK IT or BAL WATERPROOFING KIT FOR SHOWERS.
- (4) Seal back face and edges with undiluted BAL BOND SBR.
- (5) Check suitability for the intended purpose with the manufacturer. (6) Drying times will be extended, i.e. leave adhesive to dry for a
- minimum of 3 days before grouting.
  (7) When used with BAL SUPERFLEX or BAL MICROMAX2 GROUT.

(a) Do not use shower for at least 2 weeks after completion of grouting - BS 5385:Part 4

### **BACKGROUNDS / BASES**

✓
✓
✓
✓
✓
✓
✓
✓

## **USAGE: Bed Thickness / Time**

Bed Thickness ^	Open Time*	Setting Time*
3mm max	20 mins	24 hours at 20°C

\* Open time/setting time will be extended in colder temperatures, when fixing to impervious backgrounds or when fixing tiles of low porosity.

# **COVERAGE**

Area	Trowel	Coverage ^	
Dry Wall	Round Notched	0.76m <sup>2</sup> per litre	
Wet Wall	Thin Bed Solid Bed	0.38m <sup>2</sup> per litre	

^ May vary dependent on nature and flatness of surface, and on trowel used.

# TEMPERATURE RESISTANCE\*\*

-30°C to 100°C

\*\* Cured adhesive.

#### **SURFACE PREPARATION**

#### General

Ensure surfaces to be tiled are flat, clean, dry, sound and free from contamination.

## Surface regularity:

Surface Regularity is defined as the deviation in height of the surface over short distances in a local area. In simpler terms, it is the 'flatness' or 'measure of unevenness' of the surface. It is important the surface is to SR1 (+ or – 3mm or less over a 2 meter straight edge.

Class	MAXIMUM PERMISSABLE DEVIATION FROM a 2M STRAIGHT EDGE (MM)	APPLICATION
SR1	3mm	Recommended for direct fixing of tiles and slabs with a tile adhesive

In domestic shower areas: waterproof background with BAL TANK IT, BAL WATERPROOFING KIT FOR SHOWERS or BAL WP1 TANKING SYSTEM. NOTE: Drying times will be extended, i.e. leave adhesive to dry for a minimum of 3 days before grouting.

#### **SUITABLE SURFACES include:**

# Clay Brickwork/dense concrete/blockwork walling

Allow new block mortar to dry for minimum 6 weeks before rendering /plastering. If direct fixing tiles, wall must be smooth-faced and providing the surface is sufficiently flat (SR1).

NOTE: Direct fixing of tiles to lightweight blockwork is NOT recommended.

# **Cement:sand renders**

Before tiling, ensure that the substrate is flat (SR1), free from efflorescence, laitance, dirt, polished concrete and other loose materials. Remove by the use of suitable mechanical methods (see BAL TECHNICAL DATA SHEET on BAL BOND SBR or BAL PRIME APD for priming information).

Allow the following minimum drying times:

- Concrete block walls/clay brickwork: 6 weeks

Cement:sand rendering: 2 weeks
 BAL QUICKSET CEMENT: rendering
 Rendering (bonded): 4 hours\*\*

# **BAL BOND SBR SLURRY**

\*\*1 part sand to 1 part BAL QUICKSET CEMENT by weight, mixed with appropriate amount of BAL BOND SBR pre-diluted 1:1 with clean cold water to achieve desired consistency

**BAL QUICKSET RENDER**: 2 hours

# Existing glazed ceramic tiles/glazed bricks

Ensure existing tiles/bricks are soundly bonded to a stable background that is sufficiently strong enough to support the weight of the new tiling.

If areas are loose or hollow-sounding, remove and make good with BAL QUICKSET RENDER or 1:3 cement:sand mortar over a slurry bonding coat (1 part sand to 1 part cement by weight, mixed with appropriate amount of BAL BOND SBR pre-diluted 1:1 with clean cold water to achieve desired consistency).

NOTE: Drying times will be extended, i.e. leave adhesive to dry for a minimum of 3 days before grouting.

# Fibre reinforced cement boards and lightweight tile backer boards

Install boards to BS 5385 – i.e. moisture-resistant boards screwed to seasoned timber or suitable proprietary framework at maximum 300mm centres vertically and horizontally or as per the board manufacturer's recommendations. Ensure no fixings protrude.

Do NOT seal or prime surfaces to be tiled.

NOTE: Drying times will be extended, i.e. leave adhesive to dry for a minimum of 3 days before grouting.

IMPORTANT NOTE: Obtain manufacturer's confirmation that boards are suitable for tiling and for relevant fixing instructions.

# Plywood/chipboard/ sheets (walls) (internal dry areas only)

Ensure boards (i) capable of supporting the tiled finish i.e. the weight of tiling should not exceed 30kg per m²; (ii) are sufficiently dry, rigid and securely fixed, with no protruding fixings (iii) are free from any surface contamination incompatible with adhesion. Using a suitable water resistant grade plywood, min. 12mm thick, Insert noggings to support all board edges and to allow screw (not nailed) fixing at 300mm centres. Seal timber surface on the underside and edges with undiluted BAL BOND SBR. Allow to dry. Do NOT prime surfaces to be tiled.

### Plaster (finish coat only)

Must be at least 4 weeks old before tiling. Ensure that the plaster is free from dust, laitance and friable material. If *plaster is shiny or polished*, brush thoroughly with a stiff bristled brush before priming with 2 coats of (second coat applied at 90° to the first):

- BAL PRIME APD (diluted 1:1 by volume with clean water) or
- BAL BOND SBR (diluted 1:4 by volume with clean water) Allow each coat of primer to dry.

Typical weight restrictions for tiling onto plaster i.e. a maximum weight of 20kg/m<sup>2</sup>.

NOTE: When priming, drying times will be extended, i.e. leave adhesive to dry for a minimum of 3 days before grouting.

### Plasterboard (If required)

Ensure boards are dry, securely fixed and rigid and suitable thickness used.

NOTE if the plasterboard is dot and dabbed at 300mm centres and around the perimeter, leave to dry before fixing tiles. Typical weight restrictions for tiling onto plasterboard i.e. a maximum weight of 32kg/m².

# Painted surfaces

Remove all loose and flaking paint.

Check by applying a suitable self-adhesive tape to clean dry paint surfaces. Tear off tape after 10 mins. If paint is removed with the tape, the paint is unsound.

Remove unsound paint mechanically. Do NOT use paint strippers.

NOTE: Drying times will be extended, i.e. leave adhesive to dry for a minimum of 3 days before grouting.

# APPLICATION/USAGE

Do NOT use in temperatures below 5°C or in damp conditions. If fixing larger format tiles (advised up to max. 300x300mm or fixing onto a non- porous background (e.g. tiles), drying times will be extended.

For larger size tiles contact BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE.

#### **Trowel recommendations**

Area	Trowel
Internal Dry Wall Area (up to	BAL ROUND NOTCHED
300x300mm tiles)	
Internal Wet Wall Area (up to	BAL THIN BED SOLID BED
300x300mm tiles)	
Mosaics (up to 100x100mm	BAL MOSAIC TROWEL
tiles)	

NOTE: ensure you achieve the correct of adhesive to both the background and tile in line with BS 5385, Parts 1-5.

#### Fixing procedure

- 1. Apply adhesive to wall surface and comb to required bed thickness ensuring the ribs of adhesive all run in one direction. *If fixing large (300x300mm maximum)/heavily-patterned tiles, apply additional adhesive to tile reverse* (DO NOT apply over 3mm maximum).
- 2. For *mosaics*: using a rubber tile float, press mosaics into adhesive and beat into required position, ensure joints between sheets match joints between mosaic tesserae (i.e. staggered).

For tiles: press tile firmly into the ribs of adhesive and into position, with slight twisting/sliding action to ensure optimum adhesive contact.

- 3. Fix mosaics/tiles before adhesive forms skin (typically over 20 minutes at 20°C, depending on surface porosity /atmospheric conditions). If skin has formed, remove adhesive and apply fresh layer).
- 4. Occasionally lift a mosaic/tile to check adhesive contact are 50% coverage for dry areas; min. 100% coverage for wet areas (i.e. When solid-bed fixing, leave no voids behind tiles).
- 5. Leave adequate joints between individual tiles unless self-spacing tiles used.
- 6. Install movement joints to BS 5385, Parts 1-5.
- 7. Clean off surplus adhesive from tile face and between tile joints before the adhesive has dried.

# Grouting

- 7. After tiling on porous surfaces, allow adhesive to set before grouting typically 24 hours.
- 8. Work in small areas with a BAL GROUT FLOAT or rubber squeegee. Completely fill tile joints with BAL TILE & GROUT and compact well, removing excess grout from tile surface as work proceeds.
- 9. Using a dampened sponge or sponge board, carefully clean surface diagonally to grout lines. Rinse out sponge/sponge board frequently with clean water.
- 10. When grout has set sufficiently within joints, polish tile surface with dry clean cloth OR give surface final wash with dampened sponge and clean cold water.
- 11. Wait minimum 24 hours before subjecting tiles to normal service conditions\*.
- 12. Fill movement joints and seal around baths/shower trays with BAL MICROMAX SILICONE SEALANT.

If completing a shower, do NOT use shower for at least 2 weeks (as required by BS 5385: Part 4, clause 7.2.1).

If grouting in food preparation areas or Power showers or wherever waterproof grout required, use a suitable BAL Epoxy grout i.e. BAL EASYPOXY AG. Do NOT use BAL TILE & GROUT.

# HEALTH & SAFETY INFORMATION / GOOD PRACTICE ADVICE

For detailed information and safety guidance, please refer to Product Material Safety Data Sheet [MSDS].

#### **TECHNICAL ADVISORY SERVICE**

For free expert guidance on use of this product, or any aspect of tiling, contact the BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE on Tel: 01782 591120 or 0845 600 1 222 or Fax: 01782 591121.

#### **POWERSPEC**

A unique computerised online specification system for the design and installation of ceramic, mosaic and natural stone tiling.

Visit www.powerspeconline.com

#### **SHELF LIFE**

12 months under normal dry conditions. Protect from frost and damp.

#### **QUALITY AND ENVIRONMENTAL STANDARDS**

Manufacturing quality assurance standards conform to BS EN ISO 9001. Satisfies the environmental management requirements and operational scope of ISO 14001.

#### **25 YEAR GUARANTEE**

All BAL products are supplied with a 25 year product guarantee to be free from manufacturing defects and to be fit for purpose. The guarantee covers materials replacement costs and labour.

This guarantee is subject to use of product in accordance with BAL's instructions and technical data, and good working practice. No liability can be accepted for any loss or damage arising from incorrect use of products or poor workmanship, over which BAL has no control. 10 year anti-fungal guarantee subject to regular cleaning.

Contact BAL Marketing Department for full details.

# **CONDITIONS OF SALE**

Sold subject to the Company's Conditions of Sale. *Available on request.* 

For sales and technical queries, contact:

#### **BUILDING ADHESIVES LTD**

Longton Road, Trentham, Stoke-on-Trent, ST4 8JB, England www.bal-adhesives.com

Sales

Tel: +44 (0) 1782 591160 Fax: +44 (0) 1782 591131

Technical

Tel:+44 (0) 1782 591120 or +44 (0) 845 600 1 222 Fax: +44 (0) 1782 591121

.... . . (0, =: 0= 00

Ireland

Unit 622, Phase III Northwest Business Park Ballycoolin, Dublin 15, Ireland Tel: +353 (0) 1 880 9210

Fax: +353 (0) 1 880 9211

NOTE: BAL reserves the right to update instructions, technical data and other information at any time without notice.

PorcelBond Plus™ is a trademark of Building Adhesives Ltd